

Project: [REDACTED]

Notebook Number: _____

Mixing Pt Bath

2nd Pt Remo

For 4 Ltrs

Add 4 * 15 grams KOH = 60 gr KOH

Add 4 * 19.5 = 78 grams Pt A salt

Mixed 18 Liters

pH \approx ~~11.97~~ 11.951st Run old water 1.88 Amps DC \rightarrow 7.2 \pm @ 25°C

2nd Run w 200 Å seed layer # 05

Exceeded 9.9 \pm only reached 1.6 Å

Aborted Run

Readjusted Head to fully touch solution

For water # 04 200 Å seed

initial resistance for High

@ 9.9 \pm only \approx 1.6 ÅAs Pt deposited resistance \downarrow and \pm \downarrow At end of Run \approx 8.4 \pm

Read and Understood By:

Signature _____

Signature _____

Date _____

Date _____

2/10

Project:

PT N. K.

Notebook Number:

Diffuser at 15 mm

Changing to

Changed recipe to 2 step

Low Current 1.4 A for 1 A-min

Plate 1.55 A for 4.93 A-min

10:35 AM Pump 59% @ 5.0 GPM

Trial

Run A ← water 03 200 A° 25°C

5.93 A-MIN @ 1.88 A (1.4 A per plate for 1 A-min)

Total water plates ≈ 7

Un. formula $\approx 10\%$

Read and Understood By:

Signature

Signature

Date

Date

Project: _____

3/10

Notebook Number: _____

Run # 1 200 Å seed T₂N 5.3 mA/cm²
crater # 6

Voltage P₁ seed = 6.3 25°C

V_{plate} = 7.26 5 GPM

Small amount of cracking near fingers

Diffusion spacing @ 10 mm

Run # 2 water 01 600 Å ~~T₂N~~ T₂N 25°C
Current at 2 A = mA/cm² 5 GPM

V_{pre} = 5.5

V_{plate} 7.13

Total water plated = 9

13:40 HRS Added 550 mls H₂O

pH = 11.72

pump speed > 60%

Run # 3 water # 10 Seed = 600 Å T₂O₂

V_{pre} 7.12

V_{plate} = 8.60

Peeling on Edge

Poor Adhesion

2 Amps

Read and Understood By: _____

Signature _____

Signature _____

Date _____

Date _____

Project: _____

Notebook Number: _____

Run # 8 wafer # 21 200 Å seed Ta N Bar

Recipe - PT-5 25°C

 $V_{pre} = 8.03$ $V_{plate} = 8.29$

Peel at @ edges

Run # 9 wafer 24 600 Å seed Ta N

Recipe 7 T = 25

 $V_{pre} =$ $V_{plate} = 8.2$

Peel at @ Edge

Run # 10 wafer 02 600 Å T.N

Recipe PT-5 T = 25

 $V_{pre} = 6.41$ $V_{post} = 7.28$

Total Plated = 17

Red Brown Layer?
Peel at @ Edge

Run # 11 wafer 07 200 Å seed on T.N

Recipe PT-7 T = 25

 $V_{pre} = 7.80$ $V_{post} = 9.68$

High Peeling

Read and Understood By: _____

Signature _____

Signature _____

Date _____

Date _____

5/10

Project: _____

Notebook Number: _____

Run # 4 water # 7 P Low lot of Pattern

Patterned 1000 Å seed Ta N Burn

2 Amps 25 °C

V_{pre}

$V_{plate} = 7.37$

Total: 2.97 A-min

Run # 5 water # 19

500 Å seed Ta Burn

$V_{pre} = 5.96 V$

593 A-min

$V_{plate} =$

Recipe Pt-5 Rest for

Run # 6

water 20

Ta Burn

600 Å seed

Pt-7

No peeling

Run # 7

water 16

Ta 200 Å seed

Pt-7

No peeling

Read and Understood By: _____

Signature _____

Signature _____

Date

Date _____

32

1-15-82
Evolutionary
GAS Analysis
continued

6/10

Project: _____

Notebook Number: _____

~~Run # 12 Wafer # 17 200i seed~~

<u>Run #</u>	<u>wafer #</u>	<u>Seed (A)</u>	<u>Backing</u>	<u>Rear</u>	<u>Vase</u>	<u>V-post</u>	<u>Peeling</u>	<u>T</u>
2	17	200	Ta	Pt-S	8.35	8.61	Depth	25
3	18	200	Ta	Pt-7	5.74 8.31	6.83	Peeling	65
4	25	600	Ta-N	Pt-S	4.18	4.62	" "	65
5	22	200	Ta-N	Pt-7	5.54	6.84	" "	65
6	03	600	Ta-N	Pt-7	4.26	5.25	Pt film Pt Peeling	"
17	23	200	Ta-N	Pt-S	6.02	6.06		"
18	9	600	Ta-N	Pt-S	4.09	4.57		
19	8	400	Ta-N	Pt-7	4.55	5.55		

SEM Area 3mm x 1mm

5:30 PM Pump % @ 5 GPM = 60%

Read and Understood By:

Signature _____

Signature _____

Date _____

Date _____

7/10

Project:

M.1, P+

Notebook Number:

Added 3g Pt salt & 1.1 L of water

Ran 65°C all AM (No plating), cooled

Added = 1 L water @ Noon

Patterned water

Receiver	Fx I	Amp. min	Total
PT7 PL Pulse 1 on 1 off		1 1.4	2.4
PT8 PL Pulse 1 on 1 off		0 2.4	2.4
PT7		1.0 4.97	5.97
PT5		1.0 4.97	5.97
PT7		1.0 1.4	2.4
PT3		0 2.4	2.4

Read and Understood By:

Signature

Signature

Date

Date

8/10

ect: _____

Not book Number: _____

601 # red Barriers Recipe Made T Type Update

~~22~~ ~~600~~ ~~70~~ ~~PT 3 PL~~ ~~Pulse~~

9.0 Alant	600	T _a N	PT 7 PL	Also	25	
11	1000	T _a N	PT 3 PL	Pulse		1.64
15	1000	T _a	7	DC		
18	600	T _a N	3	↓		
20	1000	T _a N	7	↓	↓	

Read and Understood By: _____

Signature _____

Date _____

Pr

5

5

9/10

Project: Mot. Pt [REDACTED]

Notebook Number: _____

Visual Evaluation

Blanket markers

marker #

- | | | |
|---------|--|----------------------------------|
| 01 | Heavy Edge Peeling | Peeling of ECD Pt film
PUN Pt |
| 02 | " | " |
| 03 | Peeling (Heavy) of ECD Pt film | PUN Pt |
| 04 | " | " |
| 05 | Missing | |
| 06 | Peeling around fingers, Underlying layer is silver &
cracked (Is it Barrier or PUN Pt)
Lo.Hg like Barrier
Heavy edge peeling of Pt total film Barrier | |
| 07 | " | " |
| 08 | Little to No edge or finger peeling | |
| 09 | Heavy Finger & edge peeling near 1 finger
Remainder NO edge or finger peeling | |
| 10 | Heavy edge & finger peeling, poor adherency | |
| 11 | Little edge peeling near fingers only | |
| 12 | Cracking peeling near every finger
No edge peeling | |
| 13 | Localized edge peeling in 1 spot | |
| 14 | Localized edge peeling near fingers | |
| 15 | No peeling | |
| 16 | Little to No peeling - N.I I plate on the edge? | |
| 17 & 18 | " | " |

Read and Understood By: _____

Signature _____

Signature _____

Date _____

Date _____

Project: _____

Not book Number: _____

19 Little peel @ edge, More than 17 & 18

20 " "

21 Peel @ edge

22 " "

23 Hug peel @ edge

24 Peel @ edge

25 " "

Patterned Notes

23 Peel @ edge Localized

24 " " " "

29 No peeling

11 " "

14 Light edge peel

15 " "

16 " "

19 " "

20 " "

Read and Understood By: _____

Signature _____

Signature _____

Date _____

Date _____